Janata Mahavidyalaya ,Chandrapur Department of Physics M.Sc. II Sem-III Session- 2019-20

Quantum Dots

- Prof. G. P. Save Dept. of Physics

Outline

- Introduction
- Quantum Confinement
- QD Synthesis
 - Colloidal Methods
 - Epitaxial Growth

Introduction

Definition:

 Quantum dots (QD) are nanoparticles/structures that exhibit 3 dimensional quantum confinement, which leads to many unique optical and transport properties.



GaAs Quantum dot containing just 465 atoms.

Lin-Wang Wang, National Energy Research Scientific Computing Center at Lawrence Berkeley National Laboratory. http://www.nersc.gov

Introduction

- Quantum dots are usually regarded as semiconductors by definition.
- Similar behavior is observed in some metals. Therefore, in some cases it may be acceptable to speak about metal quantum dots.
- Typically, quantum dots are composed of groups II-VI, III-V, and IV-VI materials.
- QDs are **bandgap tunable** by size which means their optical and electrical properties can be engineered to meet specific applications.

Definition

- Quantum Confinement is the spatial confinement of electron-hole pairs (excitons) in one or more dimensions within a material.
 - Zero D Confinement Small Cube
 - 1D confinement: Quantum Wells
 - 2D confinement: Quantum Wire
 - 3D confinement: Quantum Dot
- Quantum confinement is more prominent in semiconductors because they have an energy gap in their electronic band structure.
- Metals do not have a bandgap, so quantum size effects are less prevalent. Quantum confinement is only observed at dimensions below 2 nm.

 Recall that when atoms are brought together in a bulk material the number of energy states increases substantially to form nearly continuous bands of states.



- The reduction in the number of atoms in a material results in the confinement of normally delocalized energy states.
- Electron-hole pairs become spatially confined when the diameter of a particle approaches the de Broglie wavelength of electrons in the conduction band.
- As a result the energy difference between energy bands is **increased** with decreasing particle size.



- This is very similar to the famous particle-in-a-box scenario and can be understood by examining the Heisenberg Uncertainty Principle.
- The Uncertainty Principle states that the more precisely one knows the position of a particle, the more uncertainty in its momentum (and vice versa).
- Therefore, the more spatially confined and localized a particle becomes, the broader the range of its momentum/energy.
- This is manifested as an increase in the average energy of electrons in the conduction band = increased energy level spacing = larger bandgap
- The bandgap of a spherical quantum dot is increased from its bulk value by a factor of 1/R², where R is the particle radius.*

^{*} Based upon single particle solutions of the schrodinger wave equation valid for R< the exciton bohr radius.

- What does this mean?
 - Quantum dots are bandgap tunable by size. We can engineer their optical and electrical properties.
 - Smaller QDs have a large bandgap.
 - Absorbance and luminescence spectrums are blue shifted with decreasing particle size.



Quantum Dots (QD)

- Nanocrystals (2-10 nm) of semiconductor compounds
- Small size leads to confinement of excitons (electron-hole pairs)
- Quantized energy levels and altered relaxation dynamics
- Examples: CdSe, PbSe, PbTe, InP



Quantum Dots

Absorption and emission occur at specific wavelengths, which are related to QD size



QD Synthesis: Colloidal Methods

- Example: CdSe quantum dots
- 30mg of Elemental Se and 5mL of octadecene are used to create a stock precursor Se solution.
- 0.4mL of Trioctylphosphine oxide (TOPO) is added to the Se precursor solution to disassociate and cap the Se.
- Separately, 13mg of CdO, 0.6mL of oleic acid and 10mL of octadecene were combined and heated to 225°C
- Once the CdO solution reaches 225°C, room-temperature Se precursor solution was added. Varying the amount of Se solution added to the CdO solution will result in different sized QDs.



Figure: Colloidal suspensions of CdSe quantum dots of increasing size from left (approximately 1.8-nm diameter) to right (approximately 4.0-nm diameter). Bottom: Samples viewed in ambient light vary in color from green-yellow to orange-red. Top: The same samples viewed under long-wave ultraviolet illumination vary in color from blue to yellow.

Journal of Chemcial Education. Vol. 82 No.11 Nov 2005

- Epitaxial growth refers to the layer by layer deposition/growth of **monocrystalline** films.
- A liquid or gaseous precursor condenses to form crystallites on the surface of a substrate.
- The substrate acts as a seed crystal. Its lattice structure and crystallographic orientation dictate the morphology of epitaxial film.
- Epitaxial growth techniques can be used to fabricate QD core/shell structures and QD films.

Quantum Dot Films

- QD Film thin film containing small localized clusters of atoms that behave like quantum dots.
- QD films can be highly ordered quantum dot arrays or randomly agglomerated clusters with a broad size distribution.
- The structure of choice (arrayed or disordered) depends on the particular application.



SEM image of highly order InAs QD array



AFM image of QD film containing random agglomerated clusters of InAs QDs.

Core/Shell Structures:

- Core/shell quantum dots are comprised of a luminescent semiconductor core capped by a thin shell of higher bandgap material.
- The shell quenches non-radiative recombination processes at the surface of the luminescent core, which increases quantum yield (brightness) and photostabilty.
- Core/shell quantum dots have better optical properties than organically passivated quantum dots and are widely used in biological imaging.



Jyoti K. Jaiswal and Sanford M. Simon. **Potentials and pitfalls of fluorescent quantum dots for biological imaging.** TRENDS in Cell Biology Vol.14 No.9 September 2004

- There are a variety of epitaxial methods, which each have their own subtechniques:
 - Laser Abblation
 - Vapor Phase Epitaxy (VPE)
 - Liquid Phase Epitaxy (LPE)
 - Molecular Beam Epitaxy (MBE)

Applications of QDs: Biological

 A broad absorption and narrow emission spectrum means a single excitation source can be used to excite QDs of different colors making them ideal for imaging multiple targets simultaneously.



CdSe/ZnS QDs used to image cancer cells in a live mouse.

Gao, Xiaohu. "In vivo cancer targeting and imaging with." <u>Nature Biotechnology</u> 22(2004): 8.

Applications of QDs: Biological

Bioconjugated QDs:

• The surface of QDs can be functionalized with **affinity ligands:** antibodies, peptides, or small-molecule drug inhibitors, to target specific types of cells for *in vivo* or *in vitro* imaging.

- The affinity ligands are not bound directly to the surface of the quantum dots. They are usually connected to a linker molecule referred to as a **capping ligand** or **coordinating ligand**.
- Polymers such as poly ethylene glycol (PEG) may be introduced to reduce nonspecific binding of the affinity ligands.



Applications of QDs



QDs conjugated with antibody molecules (blue) by using avidin (purple) or protein A (green) as linkers. Between 10 and 15 linker molecules can be attached covalently or electrostatically to a single QD, which facilitates the binding of many or a few antibody molecules on each QD.

Jyoti K. Jaiswal and Sanford M. Simon. **Potentials and pitfalls of fluorescent quantum dots for biological imaging.** TRENDS in Cell Biology Vol.14 No.9 September 2004

Outline

- Introduction
- Quantum Confinement
- QD Synthesis
 - Colloidal Methods
 - Epitaxial Growth
- Applications
 - Biological
 - Additional Applications

Applications of QDs: Light Emitters

- The discovery of quantum dots has led to the development of an entirely new gamut of materials for the active regions in LEDs and laser diodes.
- Indirect gap semiconductors that don't luminesce in their bulk form such as Si become efficient light emitters at the nanoscale due quantum confinement effects.
- The study of QDs has advanced our understanding of the emission mechanisms in conventional LED materials such as InGaN, the active region of blue LEDs.
- The high radiative-recombination efficiency of epitaxial InGaN is due to self-assembled, localized, In rich clusters that behave like QDs.

Additional Applications of QDs

- New applications for QDs are continuously being discovered.
- For example: Solar cells that incorporate QDs may lead to more efficient light harvesting and energy conversion.

Quantum Dot Solar Cells

Possible benefits of using quantum dots (QD):

- "Hot carrier" collection: increased voltage due to reduced thermalization
- Multiple exciton generation: more than one electron-hole pair per photon absorbed
- Intermediate bands: QDs allow for absorption of light below the band gap, without sacrificing voltage

MRS Bulletin 2007, 32(3), 236.

QDs: Collect Hot Carriers

Band structure of bulk semiconductors absorbs light having energy > E_g . However, photogenerated carriers thermalize to band edges.



- 1. Tune QD absorption (band gap) to match incident light.
- 2. Extract carriers without loss of voltage due to thermalization.



QDs: Multiple Exciton Generation

In bulk semiconductors: 1 photon = 1 exciton



Absorption of one photon of light creates one electron-hole pair, which then relaxes to the band edges. In QDs: 1 photon = multiple excitons



The thermalization of the original electron-hole pair creates another pair.

QDs: Intermediate Bands

Conventional band structure does not absorb light with energy $< E_g$



Intermediate bands in the band gap allow for absorption of low energy light



P3HT:CdSe Solar Cells



www.nano4me.org

© 2018 The Pennsylvania State University

Quantum Dots 27



www.nano4me.org

© 2018 The Pennsylvania State University

Quantum Dots 28

Thank You ...